

	Type	L #	Hits	Search Text
1	IS&R	L1	4425	(351/44,45,49,51,159,163,162,165,166,172,177) .CCLS.
2	BRS	L2	1441	and @pd>"20041001"
3	BRS	L3	892	and (layer\$4 or film\$4)
4	BRS	L4	863	and lens\$2
5	BRS	L5	664	and ((function\$4 or polar\$6 or photochrom\$6 or melanin or mirror\$4 or reflect\$6 or color\$4 or IR or infrared or hardcoat\$4 or hard-coat\$4 or coat\$4 or anti-reflect\$6 or anti-fog\$6) with (layer\$4 or film\$4))
6	BRS	L6	564	and ((function\$4 or polar\$6 or photochrom\$6 or melanin or mirror\$4 or reflect\$6 or color\$4 or IR or infrared or hardcoat\$4 or hard-coat\$4 or coat\$4 or anti-reflect\$6 or anti-fog\$6) near3 (layer\$4 or film\$4))
7	BRS	L7	126	and (inject\$4 near3 (mold\$4 or mould\$4))

	Type	L #	Hits	Search Text	DBs
1	BRS	L1	108 673	(optic\$4 or lens\$2) with (hard-coat\$4 or coat\$4 or hardcoat\$4 or anti-reflect\$6 or anti-fog\$6)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
2	BRS	L2	546 563	(optic\$4 or lens\$2) with (polariz\$6 or photochrom\$6 or melanin or mirror\$4 or reflect\$6 or color\$4 or infrared or ir of functional\$2)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
3	BRS	L4	315 386	1 or 2	US-PGPUB; USPAT
4	BRS	L5	317 721	3 and @pd>"20041001"	US-PGPUB; USPAT
5	BRS	L6	186 30	5 and ((polariz\$6 or photochrom\$6 or melanin or mirror\$4 or reflect\$6 or color\$4 or infrared or ir or functional\$2) near3 (film\$4 or layer\$4))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
6	BRS	L7	272 00	5 and ((hard-coat\$4 or coat\$4 or hardcoat\$4 or anti-reflect\$6 or anti-fog\$6) near3 (film\$4 or layer\$4))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
7	BRS	L8	374 00	6 or 7	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
8	BRS	L9	117 6	8 and (lens\$2 near3 (film\$2 or layer\$3))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
9	BRS	L10	198	9 and ((siz\$2 or diameter\$2 or circumferenc\$4) near3 (film\$3 or layer\$4))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB

	Type	L #	Hits	Search Text	DBs
10	BRS	L11	35	10 and ((optic\$4 or lens\$2) near3 (hard-coat\$4 or coat\$4 or hardcoat\$4 or anti-reflect\$6 or anti-fog\$6))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
11	BRS	L12	149	10 and ((optic\$4 or lens\$2) near3 (polariz\$6 or photochrom\$6 or melanin or mirror\$4 or reflect\$6 or color\$4 or infrared or ir of functional\$2))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
12	BRS	L13	155	11 or 12	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB
13	BRS	L14	30	13 and (inject\$3 near3 (mold\$4 or mould\$4))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB